

Test Report

No. : CE/2007/B5587A Date : 2007/12/12 Page : 1 of 5

SHINKONG SYNTHETIC FIBERS CORPORATION
8F., NO. 123, SEC. 2, NANKING E. RD., TAIPEI, TAIWAN, R. O. C.
TEL : +886-3-4932131 Ext. 1732 FAX : +886-3-4915763



The following sample(s) was/were submitted and identified by/on behalf of the client as :

Sample Description : THERMOPLASTIC POLYESTER RESIN
Style/Item No. : SHINITE[®] PBT (D202BK, D202G08BK, D202G10BK, D202G15BK, D202G20BK, D202G30BK)
Manufacturer/Vendor : SHINKONG SYNTHETIC FIBERS CORPORATION
Country of Origin : TAIWAN
Sample Receiving Date : 2007/11/21
Testing Period : 2007/11/21 TO 2007/11/28

=====
Test Requested : In accordance with the RoHS Directive 2002/95/EC, and its amendment directives.
Test Method : With reference to IEC 62321, Ed.1 111/54/CDV Procedures for the Determination of Levels of Regulated Substances in Electrotechnical Products.
(1) Determination of Cadmium by ICP-AES.
(2) Determination of Lead by ICP-AES.
(3) Determination of Mercury by ICP-AES.
(4) Determination of Hexavalent Chromium for non-metallic samples by UV/Vis Spectrometry.
(5) Determination of PBB and PBDE by GC/MS.
Test Result(s) : Please refer to next page(s).

Chenyu Kung / Operation Manager
Signed for and on behalf of
SGS TAIWAN LTD.
Chemical Laboratory – Taipei

Test Report

No. : CE/2007/B5587A

Date : 2007/12/12

Page : 2 of 5

SHINKONG SYNTHETIC FIBERS CORPORATION

8F., NO. 123, SEC. 2, NANKING E. RD., TAIPEI, TAIWAN, R. O. C.

TEL : +886-3-4932131 Ext. 1732 FAX : +886-3-4915763



Test results by chemical method (Unit: mg/kg)

Test Item (s):	Method (Refer to)	Result	MDL
		No.1	
Cadmium (Cd)	(1)	n.d.	2
Lead (Pb)	(2)	11	2
Mercury (Hg)	(3)	n.d.	2
Hexavalent Chromium Cr(VI) by alkaline extraction	(4)	n.d.	2
Sum of PBBs	(5)	n.d.	-
Monobromobiphenyl		n.d.	5
Dibromobiphenyl		n.d.	5
Tribromobiphenyl		n.d.	5
Tetrabromobiphenyl		n.d.	5
Pentabromobiphenyl		n.d.	5
Hexabromobiphenyl		n.d.	5
Heptabromobiphenyl		n.d.	5
Octabromobiphenyl		n.d.	5
Nonabromobiphenyl		n.d.	5
Decabromobiphenyl		n.d.	5
Sum of PBDEs (Mono to Nona) (Note 4)		n.d.	-
Monobromobiphenyl ether		n.d.	5
Dibromobiphenyl ether		n.d.	5
Tribromobiphenyl ether		n.d.	5
Tetrabromobiphenyl ether		n.d.	5
Pentabromobiphenyl ether		n.d.	5
Hexabromobiphenyl ether		n.d.	5
Heptabromobiphenyl ether		n.d.	5
Octabromobiphenyl ether		n.d.	5
Nonabromobiphenyl ether	n.d.	5	
Decabromobiphenyl ether	n.d.	5	
Sum of PBDEs (Mono to Deca)	n.d.	-	

TEST PART DESCRIPTION:

NO.1 : BLACK PLASTIC PELLETS

Note : 1. mg/kg = ppm

2. n.d. = Not Detected

3. MDL = Method Detection Limit

4. According to 2005/717/EC DecaBDE is exempt.

5. "-" = Not Regulated


Test Report

No. : CE/2007/B5587A Date : 2007/12/12 Page : 3 of 5

SHINKONG SYNTHETIC FIBERS CORPORATION
 8F., NO. 123, SEC. 2, NANKING E. RD., TAIPEI, TAIWAN, R. O. C.
 TEL : +886-3-4932131 Ext. 1732 FAX : +886-3-4915763



- 1) These samples were dissolved totally by pre-conditioning method according to below flow chart.
 (Cr⁶⁺ test method excluded)
- 2) Name of the person who made measurement: Troy Chang
- 3) Name of the person in charge of measurement: Chenyu Kung



Sample Material	Digestion Acid
Steel, copper, aluminum, solder	Aqua regia, HNO ₃ , HCl, HF, H ₂ O ₂
Glass	HNO ₃ /HF
Gold, platinum, palladium, ceramic	Aqua regia
Silver	HNO ₃
Plastic	H ₂ SO ₄ , H ₂ O ₂ , HNO ₃ , HCl
Others	Any acid to total digestion

Test Report


No. : CE/2007/B5587A Date : 2007/12/12

Page : 4 of 5

SHINKONG SYNTHETIC FIBERS CORPORATION
 8F., NO. 123, SEC. 2, NANKING E. RD., TAIPEI, TAIWAN, R. O. C.
 TEL : +886-3-4932131 Ext. 1732 FAX : +886-3-4915763



PBB/PBDE analytical FLOW CHART



Test Report

No. : CE/2007/B5587A

Date : 2007/12/12

Page : 5 of 5

SHINKONG SYNTHETIC FIBERS CORPORATION

8F., NO. 123, SEC. 2, NANKING E. RD., TAIPEI, TAIWAN, R. O. C.

TEL : +886-3-4932131 Ext. 1732 FAX : +886-3-4915763



** End of Report **